



A Heytex group company

STYLE: C13604  
DragonTuf  
Vinyl Laminated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 13 oz. / yd.<sup>2</sup>

Grab Tensile

ASTM D-751 210 x 225 lbs.

Strip Tensile

ASTM D-751 130 x 135 lbs. / in.  
Procedure B

Tongue Tear

ASTM D-751 40 x 50 lbs.  
8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 60 x 40 lbs.

Adhesion

ASTM D-751 20 lbs. / in.  
RF Weld

Low Temperature

ASTM D-2136 -40 ° F

Flame Resistance

Cal. Fire Marshal-Title 19 Pass  
NFPA 701 Pass  
FAR 25.853 (a) Pass

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466  
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301  
www.bondcote.com ISO 9001: 2008 Certified