



A Heytex group company

STYLE: C14403
Super 14
Vinyl Coated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 14 oz. / yd.²

Grab Tensile

ASTM D-751 450 x 425 lbs.

Strip Tensile

ASTM D-751 260 x 250 lbs. / in.
Procedure B

Tongue Tear

ASTM D-751 90 x 80 lbs.
8x10 Specimen @ 12 in. / min.

Adhesion

ASTM D-751 10 lbs. / in.
RF Weld

Puncture Resistance

ASTM D-4833 185 lbs.

Hydrostatic Resistance

ASTM D-751 700 psi
Procedure A

Low Temperature

ASTM D-2136 -40 ° F

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
www.bondcote.com ISO 9001: 2008 Certified