

STYLE: C18402
18 oz. Flame Retardant
Vinyl Coated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 18 oz. / yd.²

Grab Tensile

ASTM D-751 450 x 425 lbs.

Strip Tensile

ASTM D-751 225 x 200 lbs. / in.
 Procedure B

Tongue Tear

ASTM D-751 80 x 70 lbs.
 8x10 Specimen @ 12 in. / min.

Adhesion

ASTM D-751 10 lbs. / in.
 RF Weld

Puncture Resistance

ASTM D-4833 185 lbs.

Hydrostatic Resistance

ASTM D-751 700 psi
 Procedure A

Low Temperature

ASTM D-2136 - 40° F

Mildew Resistance

ASTM G-21 No Growth

UV Resistance

ASTM G-53 1000 Hours

Flame Resistance

Cal. Fire Marshal-Title 19 Pass
 NFPA 701 Pass
 FAR 25.853 (a) Pass

Date Issued: April 21, 2011

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
 P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
 www.bondcote.com ISO 9001: 2008 Certified