



A Heytex group company

**STYLE: G18468**  
**Vinyl Coated Polyester**

**TYPICAL PERFORMANCE PROPERTIES**

Total Weight

ASTM D-751 18 oz. / yd.<sup>2</sup>

Grab Tensile

ASTM D-751 450 x 340 lbs.

Strip Tensile

ASTM D-751 225 x 190 lbs. / in.  
Procedure B

Tongue Tear

ASTM D-751 90 x 80 lbs.  
8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 50 x 40 lbs.

Adhesion

ASTM D-751 10 lbs. / in.  
RF Weld

Puncture Resistance

ASTM D-4833 190 lbs.

Hydrostatic Resistance

ASTM D-751 700 psi  
Procedure A

Low Temperature

ASTM D-2136 -55 ° F

Mildew Resistance

ASTM G-21 No Growth

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466  
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301  
www.bondcote.com ISO 9001: 2008 Certified