



A Heytex group company

STYLE: G22415
Vinyl Coated Polyester

TYPICAL PERFORMANCE PROPERTIES

Total Weight

ASTM D-751 22 oz. / yd.²

Grab Tensile

ASTM D-751 480 x 500 lbs.

Strip Tensile

ASTM D-751 320 x 310 lbs. / in.
Procedure B

Tongue Tear

ASTM D-751 160 x 150 lbs.
8x10 Specimen @ 12 in. / min.

Trap Tear

ASTM D-751 60 x 60 lbs.

Adhesion

ASTM D-751 10 lbs. / in.
RF Weld

Puncture Resistance

ASTM D-4833 250 lbs.

Hydrostatic Resistance

ASTM D-751 800 psi
Procedure A

Low Temperature

ASTM D-2136 -40 ° F

Mildew Resistance

ASTM G-21 No Growth

Date Issued: September 6, 2010

We believe this information is the best currently available, but assume no obligation or liability in connection therewith. We make no guarantee of results and no representation that the material is fit for any particular purpose. There are NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY, unless specified in writing and signed by BondCote Corporation

P: 540.980.4461 | 800.255.9338 | F: 540.980.4466
P.O. Box 729, 509 Burgis Avenue, Pulaski, VA 24301
www.bondcote.com ISO 9001: 2008 Certified